

## COSMOSHINE<sup>®</sup> Low Fringe Type A2330

Property		Unit	Product type		Test Method
			A2330		
Thickness		$\mu$ m	125	188	JIS C-2318
Transparency		%	91.6	91.6	JIS K-7105
Haze		%	2.5	2.5	JIS K-7105
Friction coefficient	MD	(F/B)	0.50	0.60	JIS K-7125
	TD		0.39	0.44	
Tensile Strength	MD	MPa	227	200	JIS C-2318
	TD		264	240	
Breaking Elongation	MD	%	135	160	JIS C-2318
	TD		83	95	
Heat Shrinkage	MD	%	1.0	0.8	JIS C-2318
	TD		0.6	0.4	
HC adhesion	EXF-0203		100/100	100/100	Dainichi Seika Color & Chemicals Mfg. Co.,ltd.
	EXF-018		100/100	100/100	
HC rainbow	EXF-0203		○	○	
	EXF-018		○	○	

Remark : Above data is typical value,not guaranteed.

TOYOBO CO., LTD.  
International Industrial Films Sales Department

Head office:  
2-8, Dojima Hama 2-Chome, Kita-Ku, Osaka, 530-8230 JAPAN  
TEL.+81-6-6348-4123  
FAX.+81-6-6348-4160

Tokyo Branch:  
Sumitomo Corporation Kyobashi Building, 17-10, Kyobashi 1-chome,  
Chuo-ku, Tokyo 104-8345, Japan  
TEL.+81-3-6887-8898  
FAX.+81-3-6887-8894